## BRICKTEXT





Scandiano, 10/17/2016

Centro di Ricerca, Sperimentazione, Consulenza e Controlle Quelità

TEST REQUESTED BY:

**MADE +39** 

Confidential Test Report N. 4539/2016 /I

Our ref.num.: 18458
Date of request: 10/11/2016

TEST SUBJECT MATERIAL

Identified by client as:

" Paver tiles 9x30 cm marked

Serie BRICK"

Source

Submitted to Laboratory by Client

**Date Received** 

10/12/2016

Time of test execution

start: 10/14/2016 end: 10/14/2016

Detailed of test / method description / test procedure

BOT 3000 "Dynamic Coefficient of Friction (DCOF)" (Ref. 9.6, Standard ANSI A137.1:2012)

The report relates only to the sample(s) tested. This report must not be reproduced in part without the written permission of Main Laboratory Sassuolo, nor used in any way as to lead to misrepresentation of the results or their implications.

# BRICKTEXT





Confidential Test Report N.

4539/2016 /I

Page 2 of 2

Date 10/17/2016

**MADE +39** 

Test specimen

" Paver tiles 9x30 cm

marked:

Serie BRICK"

### BOT 3000 "Dynamic Coefficient of Friction (DCOF)" (Ref. 9.6, Standard ANSI A137.1:2012)

TEST PROCEDURE: must be used sensor SBR rubber with characteristics standardized (par. 9.6.1.1.2 and note 3).

Sensor SBR must be controlled using a surface standard before the test.

Three (3) pieces of tile are tested in all four directions (1-2-3-4).

Testing was done in the wet condition using 0.05% Sodium-Lauryl Sulfate (SLS) in water

Testing was conducted in a laboratory at temperature of 20±2 °C and 50±5% relative humidity. Instrument used is BOT 3000 of the Regan Scientific Instruments.

### **Dynamic Coefficient**

### Test conditions: wet surface (solution SLS 0,05 %), rubber sensor

		Position			
No.	1	2	3	4	Average
1	0,44	*n.e.	0,46	*n.e.	0,45
2	0,44	*n.e.	0,49	*n.e.	0,47
3	0,46	*n.e.	0,48	*n.e.	0,47

DCOF wet of friction Standard Tiles

Before the test 0,30 After the test 0,29

<sup>\*</sup> not executed because not possible given the size of the sample

